

## Matt varnish 688

For supplementary coating if matt effects should be achieved. This varnish can be used both wet on dry and wet in wet. In case of using printing plates with high ink coverage, we recommend to use a special wet in wet matt varnish (matt varnish 1360).

### Characteristics:

- increases matt effect on printed matters
- improves rub resistance
- can be used on full surface (without water) or for a partial varnishing
- normal drying time; adding 2 % dryer 452 or 3 % Grafo Drier for a partial varnishing with water, drying can be accelerated

### Application

Can be printed on all offset inks. Pile height and powder application must be in relation to the coating film thickness and the printing substrate.

### Printing additives:

Drier	452
Thinner	455
Printing gel	348

This technical instruction sheet is designed for your information and reference. It is based on and conforms to our current knowledge. However as actual application is affected by many factors over which we have no control, we are not liable for printing failures.