

Technical Specifications

Displayline

Caliper mm	Substance g/m ²	Stiffness	
		Resonance method md	cd
Screen / Screen			
0,80	625	240	135
0,90	700	340	195
1,00	775	445	270
1,25	925	810	415
1,50	1 050	1 235	620
1,75	1 225	1 725	870
2,00	1 275	2 345	1 235
2,25	1 425	3 125	1 690
2,50	1 575	4 020	2 090

Print / Print			
0,80	625	240	135
0,90	700	340	195
1,00	775	445	270
1,25	1 000	1 065	335
1,50	1 150	1 635	530
1,75	1 275	2 375	740
2,00	1 375	3 175	1 010
2,25	1 550	4 310	1 390
2,50	1 725	5 645	1 835
3,00	1 950	5 700	2 885

white PE / white PE (S)			
1,25	850	495	250

MC / MC (S)			
1,10	850	595	355



Displayline

	Specifications	Units	Tolerances	Test methods
Caliper				
Substance	see matrix	mm	±3 %	ISO 534
Stiffness	see matrix	g/m ²	±5 %	ISO 536
Flatness	see matrix	mNm	±15 %	ISO 5629
Moisture content	0	%	-0,3/+1,5 %	SKSB
	8	%	±1,0 %	ISO 287



